

# bitumen 60-70

## Bitumen 60-70 Specification / Properties

Bitumen grade 60-70 is best used in Normal Climates in regular temperature weather.

Property	Specification	Test Method
Softening Point	49/56	D-36
Drop in Penetration after Heating %	20 Max.	D-6 & D-5
Ductility @ 25 c	100 Min.	D-113
Flash Point C	250 Min.	D-92
Loss on Heating (wt) %	0.2 Max.	D-6
Solubility in Cs2 (wt)% n Cs2 (Wt)	99.5 Min.	D-4
Specific Gravity @ 25/25 c	1.01-1.06	D-70
Spot Test	Negative	A.A.S.H.O.T.102